

SELECTION & SPECIFICATION DATA

| | |
|----------------------------------|--|
| Generic Type | Aliphatic Acrylic-Polyester Polyurethane Satin Finish |
| Description | High build, low sheen finish that has excellent resistance to corrosion, chemicals and abrasion. Suitable for application over a number of Carboline primers and intermediates, this material provides very good weathering performance in a broad range of colors. |
| Features | <ul style="list-style-type: none"> • Outstanding performance properties in both mild and aggressive environments • High build; suitable for many two-coat systems • Approved for use in food & dairy processing plants (see Approvals NZ/AU, page 5) • Application by spray, brush or roller • Indefinite recoatability • VOC compliant to current AIM regulations • Low HAPs content version of time proven Carbothane® 133 HB |
| Colour | White and full range of AS, BS, RAL and custom tinted colours. |
| Gloss | Satin |
| Finish | Satin to Low Sheen Semi-Gloss |
| Primer | <i>Refer to Substrates & Surface Preparation</i> |
| Dry Film Thickness | 76 - 127 microns (3 - 5 mils) per coat Dry film thickness in excess of 175 microns per coat is not recommended. |
| Solids Content | By Volume 61% +/- 2% |
| Theoretical Coverage Rate | 24.0 m ² at 25 microns (978 ft ² at 1.0 mils) 8.0 m ² at 75 microns (326 ft ² at 3.0 mils) 4.8 m ² at 125 microns (196 ft ² at 5.0 mils) Allow for loss in mixing and application. |
| VOC Values | As Supplied : 324 g/l These are nominal values and may vary slightly with colour. |
| Dry Temp. Resistance | Continuous: 93°C (199°F) Non-Continuous: 120°C (248°F) |
| Limitations | When exposed to light abrasion / rubbing, the affected surface will display an increase in sheen level, resulting in a variable surface finish. |
| Topcoats | Carbothane® 130 Clear Coat where required for extreme weathering resistance or NZTA/AMA approved graffiti resistance. <i>Note: Application of Clear Coat will improve UV resistance of most colours <u>but will raise the gloss level.</u></i> |

SUBSTRATES & SURFACE PREPARATION

| | |
|----------------|--|
| General | Surfaces must be clean and dry. Employ adequate methods to remove dirt, dust, oil and all other contaminants that could interfere with adhesion of the coating. Refer to the specific primer's Product Data Sheet for detailed requirements of the specified primer. |
|----------------|--|

Carbothane 133 LH

PRODUCT DATA SHEET



SUBSTRATES & SURFACE PREPARATION

| | |
|------------------------------------|--|
| Steel | For maximum protection, abrasive blasting to a minimum of SSPC-SP 6 (AS 1627.4 Class 2), or better, with a 35-70 micron surface profile. Power or hand tool clean as minimum requirement. Prime and / or intermediate coat as recommended by your Carboline sales representative or Carboline specification. |
| Galvanized Steel | Ensure no traces of galvanizing passivation treatment (quench) are present; degrease and abrade surface. Sweep abrasive blasting is highly recommended. Refer to primer Product Data Sheet. Prime with specific Carboline primer such as Carboguard® 504 or Carboguard® 635, or as recommended by your Carboline Sales Representative. |
| Aluminum | Degrease, abrade and prime with appropriate Carboline primer as recommended by your Carboline sales representative or Carboline specification. |
| Previously Painted Surfaces | Lightly sand or abrade to roughen and degloss the surface. Existing paint must attain a minimum 3B rating in accordance with ASTM D3359 "X-Scribe" adhesion test. Prime with specific Carboline primers as recommended by your Carboline sales representative or Carboline specification. |

PERFORMANCE DATA

| Test Method | System | Results | Report # |
|---|--|--|----------|
| ASTM D4213 Scrub Resistance | 1 ct 133 LH | 0.0027 µm erosion rate after 100 cycles with abrasive scrub medium | 03403 |
| ASTM G26 Weatherometer | Blasted steel 1 ct IOZ 1 ct 133 LH | No blistering, rusting or cracking after 3500 hours | 01982 |
| ASTM G53 QUV 2500 hours with UVA 340 bulb | Blasted steel 1 ct Epoxy 1 ct 133 LH | Colour change less than 2 McAdam Units; no blistering, rusting, cracking or chalking | 03394 |
| ASTM B117 Salt Fog | Blasted steel 1 ct Epoxy Zn 1 ct 133 LH | No rusting or blistering on plane or scribe. 4000 hours | 02585 |
| ASTM D5894 QUV A Prohesion | 1 ct 133 LH | No effect on plane area and 78% gloss retention after 1008 hours wet / dry salt fog cycle | 03274 |
| ASTM D4585 Humidity | Blasted steel 1 ct IOZ 1 ct 133 LH | No rusting or blistering after 3000 hours | 02585 |
| Graffiti Resistance | Blasted steel 1 ct Epoxy 1 ct 133 LH | All markings and stains removed by solvent after exposure to: shoe polish, Sharpie Marker, crayon, lipstick, spray cans of acrylic, alkyd and epoxy. | 03395 |
| ASTM D1735 Water Fog | Blasted steel 1 ct Epoxy 1 ct 133 LH | No rusting or blistering after 8600 hours | 02061 |

Test reports and additional data available on written request.

MIXING & THINNING

| | |
|---------------|---|
| Mixing | Power mix Part A separately, then combine with Part B and power mix. DO NOT MIX PARTIAL KITS. |
|---------------|---|

MIXING & THINNING

| | |
|-----------------|---|
| Thinning | Not normally required for airless spray. Use minimum quantity of Thinner #25 required for good spray atomisation; typically 0-20% depending upon gear and conditions. For brush / roller application use Thinner #22. |
| Ratio | 4:1 by volume (Part A : Part B) |
| Pot Life | 4 Hours at 24°C and less at higher temperatures. Pot life ends when coating becomes too viscous to use. MOISTURE CONTAMINATION WILL SHORTEN POT LIFE AND CAUSE GELLATION. |

APPLICATION EQUIPMENT GUIDELINES

Listed below are general equipment guidelines for the application of this product. Job site conditions may require modifications to these guidelines to achieve the desired results.

| | |
|-------------------------------------|--|
| Spray Application (General) | This is a high solids coating and may require adjustments in spray techniques. Wet film thickness is easily and quickly achieved. The following spray equipment has been found suitable and is available from manufacturers such as Binks, DeVilbiss and Graco |
| Conventional Spray | Pressure pot equipped with dual regulators, 9.5 mm (3/8") I.D. minimum material hose, 1.8 mm (.070") I.D. fluid tip and appropriate air cap. |
| Airless Spray | Pump Ratio: 30:1 (min.)* Output: 10 lt/minute (min.) Material Hose: 9.5 mm (3/8") I.D. (min.) Tip Size: .013-.015" Output PSI: 2100-2300 Filter Size: 60 mesh *Teflon packings are recommended and available from the pump manufacturer. |
| Brush & Roller (General) | Multiple coats may be required to obtain desired appearance, recommended dry film thickness and adequate hiding. Avoid excessive rebrushing or re-rolling. For best results, tie-in within 10 minutes at 24°C. |
| Brush | Recommended for touch-up only. Use a medium, natural bristle brush. |
| Roller | Use a medium-nap synthetic roller cover with phenolic core. |

APPLICATION CONDITIONS

| Condition | Material | Surface | Ambient | Humidity |
|-----------|--------------|--------------|--------------|----------|
| Minimum | 4°C (39°F) | 4°C (39°F) | 4°C (39°F) | 0% |
| Maximum | 38°C (100°F) | 43°C (109°F) | 43°C (109°F) | 90% |
| Optimum | 18°C (64°F) | 18°C (64°F) | 18°C (64°F) | 35% |

Industry standards are for substrate temperatures to be 3°C above the dew point. This product simply requires the substrate temperature to be above the dew point.

Caution: This Product is moisture sensitive in the liquid stage and until cured. Protect from high humidity, dew and direct moisture contact until cured. Application and/or curing in humidities above maximum, or exposure to moisture from rain or dew may result in a loss of gloss and/or microbubbling of the product

Carbothane 133 LH

PRODUCT DATA SHEET



CURING SCHEDULE

| Surface Temp. | Dry to Handle | Dry to Recoat | Final Cure General |
|---------------|---------------|---------------|--------------------|
| 4°C (40°F) | 24 Hours | 24 Hours | 28 Days |
| 10°C (50°F) | 15 Hours | 15 Hours | 14 Days |
| 24°C (75°F) | 6 Hours | 6 Hours | 7 Days |
| 32°C (90°F) | NR | NR | 4 Days |
| 32°C (90°F) | 3 Hours | 3 Hours | NR |

These times are based on a 75-125 micron dry film thickness. Higher film thickness, insufficient ventilation or cooler temperatures will require longer cure times and could result in solvent entrapment and premature failure.

***Maximum recoat times are indefinite.** Surface must be clean and dry. As part of good painting practice it is recommended to test for adhesion by wiping the surface with Thinner #25. If the film shows a slight "tack" the surface is suitable for recoating without extensive surface preparation such as abrading.

Polyurethane Accelerator can be used to accelerate the film forming process in this product for conditions outside of the parameters of this data sheet. Polyurethane Accelerator is added at a rate of 5 mls per mixed litre or a maximum of 25 mls per mixed five litres. At this addition rate, Polyurethane Accelerator will accelerate the cure rate of the urethane product between 25-40% depending on the substrate temperature range and reduce the pot life of the product by approximately 40-50% of that stated on the product data sheet. With the use of Polyurethane Accelerator, this product will continue to cure at temperatures as low as -7°C.

CLEANUP & SAFETY

| | |
|--------------------|---|
| Cleanup | Use Thinner #2 or Acetone. In case of spillage, absorb and dispose of in accordance with local applicable regulations. |
| Safety | Read and follow all caution statements on this product data sheet and on the MSDS for this product. Employ normal workmanlike safety precautions. Hypersensitive persons should wear protective clothing, gloves and use protective cream on face, hands and all exposed areas. |
| Ventilation | This product contains iso-cyanate. For spray application users must have air-fed masks as directed in local regulations. Adequate ventilation must be maintained throughout application and cure to avoid build up of solvent vapours. |

PACKAGING, HANDLING & STORAGE

| | |
|---|---|
| Shelf Life | Part A: Min. 24 months at 24°C Part B: Min. 24 months at 24°C *Shelf Life: (actual stated shelf life) when kept at recommended storage conditions and in original unopened containers. |
| Shipping Weight (Approximate) | 5 Litre Kit - 9.2 kg |
| Storage Temperature & Humidity | 4°-43°C 0-90% Relative Humidity |
| Flash Point (Setaflash) | Part A: 20°C Part B: -2°C |
| Storage | Store Indoors. This product is solvent based and not affected by excursions below these published storage temperatures, down to -7°C, for a duration of no more than 14 days. Always inspect the product prior to use to make sure it is smooth and homogeneous when properly mixed. |

APPROVALS

| | |
|------------------------|---|
| Approvals NZ/AU | Food Processing NZ AsureQuality assessed & passed for food / beverage including dairy farm & factory non- incidental contact. Ref: H3111 |
|------------------------|---|

WARRANTY

Manufactured and / or distributed in Australia & New Zealand by Altex Coatings under license to Carboline Company. To the best of our knowledge the technical data contained herein is true and accurate on the date of publication and is subject to change without prior notice. User must contact Altex Coatings to verify correctness before specifying or ordering. No guarantee of accuracy is given or implied. We guarantee our products to conform to Carboline quality control. We assume no responsibility for coverage, performance or injuries resulting from use. Liability, if any, is limited to replacement of products. NO OTHER WARRANTY OR GUARANTEE OF ANY KIND IS MADE BY ALTEX COATINGS OR CARBOLINE, EXPRESS OR IMPLIED, STATUTORY, BY OPERATION OF LAW, OR OTHERWISE, INCLUDING MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. All of the trademarks referenced above are the property of Carboline International Corporation unless otherwise indicated. Altex Terms and Conditions of Trade, available at www.altexcoatings.com, apply in respect of all coating products and materials supplied, including samples.