



Sea~Zone® 60

Self Polishing Antifouling

Patented Silyl Acrylate Technology

FEATURES	RECOMMENDED USES
----------	------------------

<p>Advantages:</p> <ul style="list-style-type: none"> Developed & tested over several seasons & proven in a range of marine environments Latest generation controlled hydrolysis Silyl Acrylate Polymer technology Micro fine cuprous oxide technology Self polishing hydrolysis action retains hull smoothness, reducing drag Highly predictable and stable self-polishing characteristics that provide consistent and optimum release rates of the biocides over the life of the coating. Improved adhesion to primers, build coats and existing antifouling being repainted Compatible when applied over Altex No.5 and Coastal Copper antifouling. May be applied over other coatings – please consult the AY&B Technical Helpline. Very good static exposure performance Excellent crack resistance Controls common types of fouling for multi-season protection, depending on sailing pattern and applied system Contains only NZ-EPA green rated biocides Improved performance at lower builds <p>Approvals:</p> <ul style="list-style-type: none"> ➤ IMO Tin Free Type Approval Certificate No. 20529/BI Bureau Veritas ➤ Lloyds Register – Recognised TBT Free Cert No. MNDE/2019/9019. ➤ HSNO Approval Number HSR101262 Altex Ablative Antifouling Coating SZ RTU 	<p>Sea~Zone® 60 Antifouling is a new generation Silyl Acrylate formulation that protects hulls from marine growth through a self polishing hydrolysis action. The silyl acrylate, cuprous oxide and co-biocide combination provides outstanding protection that has exceeded side by side raft trials against traditional ablative cuprous oxide based formulations. Extensive testing has proven Sea~Zone® 60 to be at the leading edge of antifouling technology.</p> <p>Sea~Zone® 60 is the ideal anti-fouling coating for Pleasure craft of virtually any description, for use in a range of waters:</p> <ul style="list-style-type: none"> Boats that are frequently used, or those moored for long periods Vessels travelling at high speeds as well as cruising yachts High tidal flow mooring locations Both Maintenance repainting and new work Suitable for tropical waters through to the cooler waters of the South Pacific <p><i>Note: Because self polishing antifouling work by slowly releasing fresh biocides, the amount of product applied has a direct bearing on system life and performance.</i></p> <p><i>One coat - per recommended spreading rate (see below) is designed to provide approximately 12 months protection in average conditions.</i></p> <p><i>Typically, two spray applied coats (@75µms DFT each), or three roller applied coats (@ 50µms DFT each) are required for two seasons protection.</i></p> <p>Do NOT apply to aluminium alloy surfaces</p>
--	---

SPECIFICATION DATA

<p>Coating Type: Patented Silyl Acrylate polymer</p> <p>Colour: Viking Red, Blackstone, Fiord Blue</p> <p><i>Note: Colours will change once immersed for 3-4 weeks – typically a lightening in tone.</i></p> <p>Packaging: 4 litre can only</p> <p>Flash Point: 27°C Setaflash</p> <p>Mix Ratio: N/A – single component</p> <p>Pot Life: N/A</p> <p>Thinner: Thinning Solvent #10</p> <p>(Do NOT thin unless absolutely necessary)</p> <p>Clean Up: Thinning Solvent #10</p> <p>Storage: Store under cool dry conditions</p> <p>Shelf Life: 12 months when correctly stored</p>	<p>Density: 1.75 kg per litre</p> <p>VOC: 381g per litre</p> <p>Volume Solids: 55±2%</p> <p>Theoretical Coverage Rate: 7.3 sq metres per litre at 75 microns dry</p> <p>Recommended Film Thickness Per Coat: 137 microns wet to obtain 75 microns dry</p> <p>Two to three coats recommended</p> <p>Application: Spray, brush or roller</p> <p>Dry Times (75 µm DFT / 25°C / 50% RH):</p> <table style="width: 100%; border: none;"> <tr> <td style="padding-left: 20px;">To Recoat</td> <td>Minimum - 9 hours, overnight is recommended</td> </tr> <tr> <td></td> <td>Maximum - Not critical</td> </tr> <tr> <td style="padding-left: 20px;">To Launch</td> <td>Minimum - 12 hours, overnight is recommended</td> </tr> </table> <p>(when multiple coats are applied to reinstate a full coating system, we recommend delaying re-launch for 24-48 hours to avoid strop damage)</p> <p>Maximum time to launch – not critical.</p>	To Recoat	Minimum - 9 hours, overnight is recommended		Maximum - Not critical	To Launch	Minimum - 12 hours, overnight is recommended
To Recoat	Minimum - 9 hours, overnight is recommended						
	Maximum - Not critical						
To Launch	Minimum - 12 hours, overnight is recommended						

SURFACE PREPARATION

All surfaces must be sound and free of all salts, oil, grease, dirt, loose and flaking paint, moisture and other foreign substances prior to application of Sea~Zone® 60 Antifouling.

Sea~Zone® 60 Antifouling may be applied over:

- Altex Epoxy Primer
- Altex Epoxy Barrier Undercoat
- Altex MultiPurpose Primer
- Altex PrimaShield Antifouling Sealer

Sea~Zone® 60 Antifouling may also be applied over:

- Altex No.5 Antifouling
- Altex Coastal Copper Antifouling

Refer to relevant product data sheet for further information.

May also be used with some alternative anti-corrosive and anti-fouling coatings. Consult your Altex Yacht & Boat Representative for specific recommendations regarding compatibility with existing anti-fouling systems. Refer to the AY&B Antifouling System brochure for further details relating to surface preparation & recoating.

Sea~Zone® 60 Antifouling must be applied over the epoxy bottom coatings before they have cured hard. Apply Sea~Zone® 60 Antifouling when the epoxy is tack free but still soft to finger pressure. If the epoxy has cured too hard, apply another thin coat of epoxy before applying Sea~Zone® 60 Antifouling.

Repainting: High pressure water clean (5,000 – 10,000 psi / 330 – 660 bar) to remove all marine growth, hydrolysed antifouling, salts, loose paint and any other foreign matter.

OR: Low pressure water clean (3,000 psi / 200 bar minimum) to remove all marine growth, hydrolysed antifouling, salts, loose paint and any other foreign matter.

AND - Wet sand the surface with 80 grit sandpaper to ensure total removal of any remaining contaminants, including residual hydrolysed antifouling and slime. Rinse thoroughly.

The cleaned surface, once dry should be free of any powdered antifouling residues and should be inspected for defects in the film. Existing anti-fouling must be secure and intact, and not excessively overbuilt.

Repairs to the coating system should be completed before the application of any subsequent coat of antifouling. To ensure good adhesion, any exposed primers / undercoats should be thoroughly sanded (p80 grit), dedusted & coated with the appropriate primer before application of any antifouling.

Thorough wet sanding is recommended at the waterline, as the wet / dry cycle and UV exposure can cause premature failure if brittle or crazy cracked coatings remain.

DIRECTIONS FOR USE

Mixing:

Before use, Sea~Zone® 60 must be thoroughly stirred, preferably with an air-powered mixer, to ensure a homogenous condition without any settlement remaining on the bottom of the container.

Thinning:

Sea~Zone® 60 generally does not require any thinning, except possibly in hot windy conditions. When required, thin using Altex Thinning Solvent #10. Additional coats may be required to attain the correct film thickness.

Clean-up:

Altex Thinning Solvent #10.

Important:

Film thickness control is **critical**.

Service life is a direct function of film thickness.

Application:

Sea~Zone® 60 can be applied by either conventional spray or airless spray equipment along with brush / roller application

Suggested spray equipment (guide only):

Conventional Air Spray Guide:

1.4mm to 2.2mm Fluid tip with appropriate air cap.

Airless Spray Guide:

Pump Ratio	30:1
Material Hose	3/8" I.D min
Tip Size	0.019 – 0.023

Roller:

Use a short nap (3/16" / 5mm) solvent proof roller.

Additional coats will be required to attain the correct film thickness if the coating is applied by brush or roller.

(Typically two spray applied coats (at 75 microns each) requires three roller applied coats to achieve the same film thickness)

PRECAUTIONS

Sea~Zone® 60 is flammable. Keep away from heat, sparks and open flame. Use with adequate ventilation. May cause eye and skin irritation. Do not breathe vapour or spray. Wear suitable protective clothing such as gloves and eye and face protection.

Precautions:

For DIY & Professional Use: Read and follow all the caution statements on this Product Data Sheet, the product label and the Safety Data Sheet (SDS) for health and safety information prior to use.

WWW.ALTEXBOATPAINT.COM

Head Office New Zealand
Altex Coatings Ltd
91-111 Oropi Road
Greerton, Tauranga 3112

Ph: +64 7 541 1221
Fax: +64 7 541 1310

Head Office Australia
Resene Paints (Aust) Ltd
Industrial & Marine Division
7 Production Avenue,
Molendinar
Queensland 4214
Ph: +61 7 5512 600
Fax: +61 7 5512 697

DISCLAIMER

Important Information No antifouling paint can be effective under all conditions of exposure, and the performance of this antifouling product depends on many factors beyond the control of the manufacturer, including but not limited to, variables during application and curing, climatic and environmental conditions both global and local during exposure, and acts of nature. We cannot and do not warrant that this product will be suitable for your particular purpose or application and no liability whatsoever is accepted by us. Any information provided by us is provided as a guide only, based on our field experience and raft trials. It is provided without warranty, express or implied. It is your sole responsibility to determine the suitability of the antifouling product for the use contemplated.

Ensure you have the latest product datasheet and material safety data sheet from the manufacturer or supplier. Check the data sheet issue date with the listings at www.altexcoatings.com
Altex Terms and Conditions of Trade, available at www.altexcoatings.com, apply in respect of all coating products and materials supplied, including samples.